



printlux paper 180 universal

Technical Information

➤ General information

- 180 g/m² barriere and matt coated-Paper
- bright white and matt surface
- matt surface

➤ Areas of application


- suitable for thermal and piezo printers
- for dye, pigmented and oil-based inks
- hot and cold laminating possible
- for indoor application e.g. Pop-up, photorealistic prints

➤ Processing & Handling

- please notice Handling- and Storage Conditions in our catalog or visit our homepage www.neschen.de
- storage is best to be done in the original case
- to avoid fingerprints, protective gloves are best to be worn while handling
- pigmented Ink recommended for use near windows against bleaching

➤ Advantages / Special Features

- universal
- very good print quality
- takes up high amounts of ink without "(wet-cockling)"
- opaque
- hot laminating and encapsulation possible
- dimensionally stable, quick drying
- ICC-profiles available
- for more information see the latest Neschen compatibility list (at www.neschen.de)



printlux paper 180 universal

Technical Information

➤ Technical Data

➤ Carrier:

Film type:	special InkJet-paper, white, coated
Thickness [µm]:	approx. 225 / approx. 8,8 mil
Weight [g/m²]:	approx. 180

➤ Others:

Handling/Storage Conditions:	18° to 25°C / 60° to 80° F; 40 to 65% relative humidity		
Shelf Life [Years]:	2		
Temperature Stability:	-30 to +50°C	-22 to +122°F	affixed to aluminium
Humid Climate Stability: [change/no change]	no change	2 weeks affixed to aluminium at 40°C (104°F) and 95% rel. humidity	

All tests were performed in accordance with 23/50-2, DIN 50014.

Temperatures in Fahrenheit and thicknesses in mil are given as approximate values. All data are standard values. The information in this specification sheet is based on findings obtained in practice. Because of the high number of factors which can have an effect during handling and application, customer tests will be required. A legally binding guarantee of specific properties is not to be inferred from our specifications. The information given here may be subject to change without notice. Neschen has not prepared MSDSs for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administrations's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the Neschen directions for use, these products should not present a health and safety hazard. However, use or processing of the products is manner not in a accordance with the directions for use may affect their performance and present potential health and safety hazards.

