

Work Order	4002.2
Setup-Code	210330-10372-22196-02



## **Test Report**

# ISO 22196 (Mod)

Measurement of antibacterial activity on plastics surfaces

## Test Object:

Filmolux foils versus Staphylococcus aureus DSM799 ATCC6538

Page 1 of 7



Work Order	4002.2
Setup-Code	210330-10372-22196-02

### **Report on Findings**

Client: Address:	Neschen Coating GmbH Hans-Neschen-Straße 1 31675 Bückeburg
Work order no.:	4002.2
Test object:	Filmolux foils versus Staphylococcus aureus DSM799 ATCC6538
Sample description:	Foils
Date of receipt of sample:	2021-Mar-24
Type of test:	ISO 22196-07: Plastics — Measurement of antibacterial activity on plastics surfaces
Test Germ:	Staphylococcus aureus DSM799 ATCC6538
Test laboratory:	QualityLabs BT GmbH
Address:	Neumeyerstrasse 46a 90411 Nuremberg, Germany
Setup-Code:	210330-10372-22196-02
Sample material:	Foils
No. of pages in report:	7
Report on findings Place a to the client: Recipion	and date of preparation: Nuremberg, 2021-Apr-01 ent: Neschen Coating GmbH
Laboratory Director:	

Dr. Sab

Dr. Sabine Krause, Laboratory Manager QualityLabs BT GmbH



Work Order	4002.2
Setup-Code	210330-10372-22196-02

#### **Declaration on Quality Assurance**

This investigation was performed and supervised according to the standard operating procedure "SOP zu ISO 22196 (Mod)" by QualityLabs BT GmbH. The laboratory and process are continually monitored by independent, external authorities, as well as by internal audits.

#### Archiving

A copy of the test report, a protocol of the measurement as well as the accompanying correspondence and business records are archived by QualityLabs BT GmbH. The retention period is at least 10 years.

#### **Test description**

Anti-bacterial activity is determined in accordance with a modified version of ISO 22196.

During the test, a thin liquid-film containing the bacteria  $(1.25 \times 10^4 \text{ CFU} / \text{cm}^2)$  is applied directly to the test sample (5 cm x 5 cm). To avoid desiccation a foil (4cm x 4cm, Stomacher Bags) is applied. Immediately after inoculation, the bacteria from the reference sample are separated from the sample and the enveloping foil surfaces using ultrasound and vortex devices and the number of viable germs (CFU – colony-forming units) is determined (t<sub>0</sub> value). A further set of reference samples and samples given anti-microbial treatment is incubated with bacteria in a liquid-film and the enveloping foil in a damp environment at 37°C. After a minimum of 24 hours, the bacteria are separated from the sample surfaces using ultrasound and vortex devices and the number of viable germs is determined (t<sub>24</sub> value).



Work Order	4002.2
Setup-Code	210330-10372-22196-02

#### Assessment of antimicrobial activity

A logarithmic germ reduction of  $\geq$  3 log scales of the antimicrobial sample in comparison to the respective reference is used as assessment criterion to pass the antimicrobial test.

Germ reduction [log scales]	Antibacterial activity
< 3	Not sufficient antimicrobial activity
≥ 3	Sufficient antimicrobial activity



Work Order	4002.2
Setup-Code	210330-10372-22196-02

#### **References to Testconditions**

Testconditions				
Sample size	25	cm <sup>2</sup>		
Foil size	16	cm <sup>2</sup>		
Volume Inoculum	400	μΙ		
Sample cleaning	Isopropanol	-		

#### References to deviations, preincubations, special test conditions

NONE

#### Page 5 of 7



Work Order	4002.2
Setup-Code	210330-10372-22196-02

### **Test Results**

	Sample Name	Sample Code		t <sub>0</sub> (cells/cm <sup>2</sup>	)		t <sub>24</sub> (cells/cm²)	)	Reduction [%]	Log Reduction
1	Reference (Leneta foil)	103722403210022	3.4 x 10 <sup>4</sup>	3.6 x 10⁴	3.2 x 10 <sup>4</sup>	8.0 x 10 <sup>4</sup>	8.3 x 10 <sup>4</sup>	9.0 x 10 <sup>4</sup>	-	Reference
2	6015672 filmolux soft organic	103722403210023				< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	> 99.99	> 4
3	filmolux PP gloss (specimen)	103722403210024				< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	> 99.99	> 4
4	fiomolux PP matt (specimen)	103722403210025				< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	> 99.99	> 4
5	Easy dot transparent (specimen)	103722403210026				< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	> 99.99	> 4
6	Solvoprint glass deco dusted (specimen)	103722403210027				< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	> 99.99	> 4

\*see "Interpretation of Results", page 7

Test strain	Staphylococcus aureus DSM799 ATCC6538			
Initial cell count inoculum / cm <sup>2</sup>	1.25 x 10⁴			
Initials of the editor	OS			
Measurement ended on	Apr-01-2021			



Work Order	4002.2
Setup-Code	210330-10372-22196-02

#### **Comments on test objects**

NONE

#### Interpretation of the results based on the measurements

All samples showed sufficient antibacterial efficacy against the test strain *Staphylococcus aureus* DSM799 ATCC6538 in comparison with the Leneta foil reference.

Editor: Mr. Shendi \_\_\_\_\_

Crosschecked : Mr. Karimi \_\_\_\_\_

#### References

ISO 22196-07: Plastics — Measurement of antibacterial activity on plastics surfaces

Please note: The reproduction of any part of this test report is not permitted without the written permission of QualityLabs BT GmbH. The result apply only to the samples tested.

Page 7 of 7